

Tapibel
Your carnet, our tradition

Manufacturing type	Herstellungsart	Mode fabrication	Productie methode	tufted 1/8"			
Construction	Struktur	Structure	Structuur	saxony (frisé)			
Pile composition	Polmateriaal	Couche d'usure	Poolsamenstelling	100% PA 6 - Econyl® - heatset			
Dye method	Farbgestaltung	Coloration	Kleurverwerking	solution dyed			
Secondary backing	Rückenausrüstung	Dossier	Rug	action backing			
Pile weight	Poleinsatzgewicht	Poids de velour	Poolgewicht	ISO 2424	g/m²	Matera: 1.600	(+/-)
					g/m²	Matera Primo: 2.000	(+/-)
Total weight	Gesamtgewicht	Poids total	Totaal gewicht	ISO 8543	g/m²	Matera: 2.400	(+/-)
					g/m²	Matera Primo: 2.800	(+/-)
Pile height	Polhöhe	Hauteur du velours	Poolhoogte	ISO 1766	mm	Matera: 8,0	(+/-)
					mm	Matera Primo: 9,0	(+/-)
Total height	Gesamtdicke	Epaisseur totale	Totale dikte	ISO 1765	mm	Matera: 10,0	(+/-)
					mm	Matera Primo: 11,0	(+/-)
Tuft density	Noppenzahl	Nombre de touffes	Aantal punten	ISO 1763	/m²	Matera: 147.200	(+/-)
					/m²	Matera Primo: 172.800	(+/-)
Size	Abmessung	Dimension	Afmeting		cm	400	(+/-)
Classification	Klassifikation	Classement	Gebruiksklasse	EN 1307	33 heavy commercial		
Comfort rating	Komfortklasse	Classement confort	Comfort klasse	EN 1307	LC 5		
Castor chair	Stuhllolleneignung	Chaise à roulettes	Rolstoelgeschikt	EN 985	A intensive		
					Matera: B occasional		
					Matera Primo: A intensive		
Fire resistance	Brennverhalten	Comportement feu	Brandgedrag	EN 13501-1	Cfl-S1 glued		
Permanent antistatic	Permanent Antistatisch	Antistatique permanent	Permanent antistatisch	ISO 6356	kV	≤ 2,0	
Transversal resistance	Durchgangswiderstand	Résistance transversale	Doorgangsweerstand	ISO 10965	Ω	> 10 ¹⁰	
Thermal resistance	Wärmedurchlaßwiderstand	Résistance thermique	Warmtedoorlaatweerstand	ISO 8302	m²/K/W	Matera: 0,125	TOG 1,25
					m²/K/W	Matera Primo: 0,135	TOG 1,35
Sound absorption	Schallabsorptionsgrad	Absorption phonique	Geluidsabsorptie	ISO 354	α _w	Matera: 0,20	
					α _w	Matera Primo: 0,25	
Impact sound reduction	Trittschallverbesserungsmaß	Isolation phonique	Geluidsisolatie	ISO 10140	ΔL _w	Matera: 28 dB	
					ΔL _w	Matera Primo: 31 dB	
					ΔL	Matera: 47 dB	(1000 Hz)
					ΔL	Matera Primo: 51 dB	(1000 Hz)
Colour fastness light	Lichtechtheit	Solidité à la lumière	Lichtechtheid	ISO 105 B02	≥ 7		
Rubbing fastness	Reibechtheit	Solidité au frottement	Wrijfechtheid	ISO 105 X12	≥ 5 wet/dry		



CE
23
EN 14041
DOP 000654A-001
DOP 000655A-001

Edition: 06/2022