

Technical details broadloom

Manufacturing type	Herstellungsart	Mode fabrication	Productie methode	tufted 1/10"		
Construction	Struktur	Structure	Structuur	2-ply cut pile		
Pile composition	Polmaterial	Couche d'usure	Poolsamenstelling	100% PA 6 - SDN - Econyl®		
Secondary backing	Rückenausrüstung	Dossier	Rug	action backing		
Pile weight	Poleinsatzgewicht	Poids de velour	Poolgewicht	ISO 2424	g/m²	1.200 (+/-)
Total weight	Gesamtgewicht	Poids total	Totaal gewicht	ISO 8543	g/m²	2.100 (+/-)
Pile height	Polhöhe	Hauteur du velours	Poolhoogte	ISO 1766	mm	6,5 (+/-)
Total height	Gesamtdicke	Epaisseur totale	Totale dikte	ISO 1765	mm	8,0 (+/-)
Tuft density	Noppenzahl	Nombre de touffes	Aantal punten	ISO 1763	/m²	210.000 (+/-)
Width	Breite	Largeur	Breedte		cm	400-500 (+/-)
Classification	Klassifikation	Classement	Gebruiksklasse	EN 1307	33	heavy commercial
Comfort rating	Komfortklasse	Classement confort	Comfort klasse	EN 1307	LC 4	
Castor chair	Stuhrolleneignung	Chaise à roulettes	Rolstoelgeschikt	EN 985	A	intensive
Stair suitability	Treppeneignung	Escaliers	Trappengeschikt	EN 1963	B	occasional
Fire resistance	Brennverhalten	Comportement feu	Brandgedrag	EN 13501-1	CFI-S1	glued
Permanent antistatic	Permanent Antistatisch	Antistatique permanent	Permanent antistatisch	ISO 6356	kV	≤ 2,0
Transversal resistance	Durchgangswiderstand	Résistance transversale	Doorgangsweerstand	ISO 10965	Ω	≤ 10³
Thermal resistance	Wärmedurchlaßwiderstand	Résistance thermique	Warmte-doorlaatweerstand	ISO 8302	m²/K/W	0,091 TOG 0,91
Sound absorption	Schallabsorptionsgrad	Absorption phonique	Geluidsabsorptie	ISO 354	α _w	0,20
Impact sound reduction	Trittschallverbesserungsmaß	Isolation phonique	Geluidsisolatie	ISO 10140	ΔL _w	28 dB
				ISO 10140	ΔL	45 dB (1000 Hz)
Light Fastness	Lichtechtheit	Solidité à la lumière	Lichtechtheid	ISO 105 B02	7-8	
Rubbing fastness	Reibechtheit	Solidité au frottement	Wrijftechtheid	ISO 105 X12	≥ 5	

Scan the QR code
and discover the collection.



