


Technical details carpet tiles						
Manufacturing type	Herstellungsart	Mode fabrication	Productie methode	tufted 1/10"		
Construction	Struktur	Structure	Structuur	Cut pile - Saxony		
Pile composition	Polmaterial	Couche d'usure	Poolsamenstelling	100% PA - ECONYL®		
Dye method	Farbgestaltung	Coloration	Kleurverwerking	Chromojet print		
Primary backing	Trägermaterial	Premier dossier	Tuftdoek	non-woven		
Secondary backing	Rückenausrüstung	Dossier	Rug	GREENBASE modified bitumen		
Pile weight	Poleinsatzgewicht	Poids de velour	Poolgewicht	ISO 2424	g/m²	900 (+/-)
Total weight	Gesamtgewicht	Poids total	Totaal gewicht	ISO 8543	g/m²	4-400 (+/-)
Pile height	Polhöhe	Hauteur du velours	Poolhoogte	ISO 1766	mm	5,0 (+/-)
Total height	Gesamtdicke	Epaisseur totale	Totale dikte	ISO 1765	mm	6,5 (+/-)
Tuft density	Noppenzahl	Nombre de touffes	Aantal punten	ISO 1763	/m²	198.750 (+/-)
Size	Abmessung	Dimension	Afmeting	cm 50 x 50		
Packing	Verpackung	Emballage	Verpakking	20 per box		5 m²
Classification	Klassifikation	Classement	Gebruiksklasse	EN 1307	33	heavy commercial
Comfort rating	Komfortklasse	Classement confort	Comfort klasse	EN 1307	LC 3	
Castor chair	Stuhlrolleneignung	Chaise à roulettes	Rolstoelgeschikt	EN 985	A	intensive
Dimensional stability	Dimensionstabilität	Stabilité dimensionnelle	Dimensionele stabiliteit	EN 986		
Fire resistance	Brennverhalten	Comportement feu	Brandgedrag	EN 13501-1	Bfl-S1	loose laid
Permanent antistatic	Permanent Antistatisch	Antistatique permanent	Permanent antistatisch	ISO 6356	kV	
Transversal resistance	Durchgangswiderstand	Résistance transversale	Doorgangsweerstand	ISO 10965	Ω	
Thermal resistance	Wärmedurchlaßwiderstand	Résistance thermique	Warmtedoorlaatweerstand	ISO 8302	m2/K/W	
Sound absorption	Schallabsorptionsgrad	Absorption phonique	Geluidsabsorptie	ISO 354	αw	
Impact sound reduction	Trittschallverbesserungsmaß	Isolation phonique	Geluidsisolatie	ISO 10140	ΔLw	
					ΔL	
Colour fastness light	Lichtechtheit	Solidité à la lumière	Lichtechtheid	ISO 105 B02	7	
Rubbing fastness	Reibechtheit	Solidité au frottement	Wrijfechtheid	ISO 105 X12		

Scan the QR code
and discover the
collection.







EN 1307
for use as floorcovering in buildings
(EN 14041) accordings to the
manufacturer's specification

CE
25
EN 14041
DOP 000675T-001





