

Technical details wall-to-wall

Manufacturing type	Herstellungsart	Mode fabrication	Productie methode		tufted 1/10"		
Construction	Struktur	Structure	Structuur		Cut Pile - Saxony		
Pile composition	Polmaterial	Couche d'usure	Poolsamenstelling		100% PA - ECONYL®		
Dye method	Farbgestaltung	Coloration	Kleurverwerking		Chromojet Print		
Primary backing	Trägermaterial	Premier dossier	Tuftdoek		non-woven		
Secondary backing	Rückenausrüstung	Dossier	Rug		action backing		
Pile weight	Poleinsatzgewicht	Poids de velour	Poolgewicht	ISO 2424	g/m²	1.200	(+/-)
Total weight	Gesamtgewicht	Poids total	Totaal gewicht	ISO 8543	g/m²	2.300	(+/-)
Pile height	Polhöhe	Hauteur du velours	Poolhoogte	ISO 1766	mm	6,0	(+/-)
Total height	Gesamtdicke	Epaisseur totale	Totale dikte	ISO 1765	mm	8,0	(+/-)
Tuft density	Noppenzahl	Nombre de touffes	Aantal punten	ISO 1763	/m²	213.000	(+/-)
Size	Abmessung	Dimension	Afmeting		cm	400	
Classification	Klassifikation	Classement	Gebruiksklasse	EN 1307		33	heavy commercial
Comfort rating	Komfortklasse	Classement confort	Comfort klasse	EN 1307		LC 5	
Castor chair	Stuhllolleneignung	Chaise à roulettes	Rolstoelgeschikt	EN 985		A	intensive
Stair suitability	Treppeneignung	Escaliers	Trappengeschikt	EN 1963			
Fire resistance	Brennverhalten	Comportement feu	Brandgedrag	EN 13501-1		Cfl-s1	glued
Permanent antistatic	Permanent Antistatisch	Antistatique permanent	Permanent antistatisch	ISO 6356	kV		
Transversal resistance	Durchgangswiderstand	Résistance transversale	Doorgangsweerstand	ISO 10965	Ω		
Thermal resistance	Wärmedurchlaßwiderstand	Résistance thermique	Warmtedoorlaatweerstand	ISO 8302	m²/K/W		
Sound absorption	Schallabsorptionsgrad	Absorption phonique	Geluidsabsorptie	ISO 354	αw		
Impact sound reduction	Trittschallverbesserungsmaß	Isolation phonique	Geluidsisolatie	ISO 10140	ΔLw		
				ISO 10140	ΔL		
Colour fastness light	Lichtechtheit	Solidité à la lumière	Lichtechtheid	ISO 105 B02		7	
Rubbing fastness	Reibechtheit	Solidité au frottement	Wrijftechtheid	ISO 105 X12			

Scan the QR code
and discover the
collection.



EN 1307

for use as floorcovering in buildings
(EN 14041) according to the
manufacturer's specification



25

EN 14041
DOP 000675A-001

