


Technical details wall-to-wall

Manufacturing type	Herstellungsart	Mode fabrication	Productie methode	tufted 1/10"	
Construction	Struktur	Structure	Structuur	structured loop pile	
Pile composition	Polmateriaal	Couche d'usure	Poolsamenstelling	100% PA 6 - Econyl®	
Dye method	Farbgestaltung	Coloration	Kleurverwerking	solution dyed	
Primary backing	Trägermaterial	Premier dossier	Tuftdoek	non-woven	
Secondary backing	Rückenausrüstung	Dossier	Rug	action backing	
Pile weight	Poleinsatzgewicht	Poids de velour	Poolgewicht	ISO 2424	g/m² 650 (+/-)
Total weight	Gesamtgewicht	Poids total	Totaal gewicht	ISO 8543	g/m² 1.950 (+/-)
Pile height	Polhöhe	Hauteur du velours	Poolhoogte	ISO 1766	mm 4,0 (+/-)
Total height	Gesamtdicke	Épaisseur totale	Totale dikte	ISO 1765	mm 6,0 (+/-)
Tuft density	Noppenzahl	Nombre de touffes	Aantal punten	ISO 1763	/m² 192.000 (+/-)
Size	Abmessung	Dimension	Afmeting	cm 400	
Classification	Klassifikation	Classement	Gebruiksklasse	EN 1307	33 general commercial
Comfort rating	Komfortklasse	Classement confort	Comfort klasse	EN 1307	LC 1
Castor chair	Stuhlrolleneignung	Chaise à roulettes	Rolstoelgeschikt	EN 985	A intensive
Stair suitability	Treppeneignung	Escaliers	Trappengeschikt	EN 1963	A intensive
Fire resistance	Brennverhalten	Comportement feu	Brandgedrag	EN 13501-1	Bfl-S1 glued
Permanent antistatic	Permanent Antistatisch	Antistatique permanent	Permanent antistatisch	ISO 6356	kV ≤ 2,0
Transversal resistance	Durchgangswiderstand	Résistance transversale	Doorgangsweerstand	ISO 10965	Ω ≥ 10¹⁰
Thermal resistance	Wärmedurchlaßwiderstand	Résistance thermique	Warmtedoorlaatweerstand	ISO 8302	m²/K/W 0,078
Sound absorption	Schallabsorptionsgrad	Absorption phonique	Geluidsabsorptie	ISO 354	α _w 0,15
Impact sound reduction	Trittschallverbesserungsmaß	Isolation phonique	Geluidsisolatie	ISO 10140	ΔL _w 25 dB
			ISO 10140	ΔL	(1000 Hz)
Light fastness	Lichtechtheit	Solidité à la lumière	Lichtechtheid	ISO 105 B02	≥ 7
Rubbing fastness	Reibechtheit	Solidité au frottement	Wrijfechtheid	ISO 105 X12	≥ 5 wet/dry

Scan the QR code
and discover the collection.



EN 1307
for use as floorcovering
in buildings (EN 14041)
according to the
manufacturer's specification

CE
22
EN 14041
DOP 000553A-003

