

Technical details wall-to-wall

Manufacturing type	Herstellungsart	Mode fabrication	Productie methode	tufted 1/10"		
Construction	Struktur	Structure	Structuur	structured loop pile		
Pile composition	Polmaterial	Couche d'usure	Poolsamenstelling	100% PA 6 - Econyl®		
Dye method	Farbgestaltung	Coloration	Kleurverwerking	50% SD - 50% space dyed		
Primary backing	Trägermaterial	Premier dossier	Tuftdoek	non-woven		
Secondary backing	Rückenausrüstung	Dossier	Rug	action backing		
Pile weight	Poleinsatzgewicht	Poids de velour	Poolgewicht	ISO 2424	g/m²	620 (+/-)
Total weight	Gesamtgewicht	Poids total	Totaal gewicht	ISO 8543	g/m²	1.900 (+/-)
Pile height	Polhöhe	Hauteur du velours	Poolhoogte	ISO 1766	mm	4,0 (+/-)
Total height	Gesamtdicke	Epaisseur totale	Totale dikte	ISO 1765	mm	6,5 (+/-)
Tuft density	Noppenzahl	Nombre de touffes	Aantal punten	ISO 1763	/m²	190.000 (+/-)
Size	Abmessung	Dimension	Afmeting	cm 400		
Classification	Klassifikation	Classement	Gebruiksklasse	EN 1307	33	heavy commercial
Comfort rating	Komfortklasse	Classement confort	Comfort klasse	EN 1307	LC 2	
Castor chair	Stuhlrolleneignung	Chaise à roulettes	Rolstoelgeschikt	EN 985	A	intensive
Stair suitability	Treppeneignung	Escaliers	Trappengeschikt	EN 1963	A	intensive
Fire resistance	Brennverhalten	Comportement feu	Brandgedrag	EN 13501-1	Bfl-S1	glued
Permanent antistatic	Permanent Antistatisch	Antistatique permanent	Permanent antistatisch	ISO 6356	kV	≤ 2,0
Transversal resistance	Durchgangswiderstand	Résistance transversale	Doorgangsweerstand	ISO 10965	Ω	≤ 10⁹
Thermal resistance	Wärmedurchlaßwiderstand	Résistance thermique	Warmtedoorlaatweerstand	ISO 8302	m²/K/W	0,066
Sound absorption	Schallabsorptionsgrad	Absorption phonique	Geluidsabsorptie	ISO 354	α _w	0,15
Impact sound reduction	Trittschallverbesserungsmaß	Isolation phonique	Geluidsisolatie	ISO 10140	ΔL _w	23 dB
				ISO 10140	ΔL	35 dB (1000 Hz)
Colour fastness light	Lichtechtheit	Solidité à la lumière	Lichtechtheid	ISO 105 B02	6-7	
Rubbing fastness	Reibechtheit	Solidité au frottement	Wrijftechtheid	ISO 105 X12	4-5	
Water fastness	Wasserechtheit	Solidité à l'eau	Waterechtheid	ISO 105 E01	4-5	colour/staining

Scan the QR code
and discover the collection.



EN 1307
for use as floorcovering
in buildings (EN 14041)
according to the
manufacturer's specification

CE
20
EN 14041
DOP 000622A-001

ECONYL®
ENDLESS POSSIBILITIES

TWISE

