


## Technical details wall-to-wall

|                        |                             |                         |                         |                |                    |                    |
|------------------------|-----------------------------|-------------------------|-------------------------|----------------|--------------------|--------------------|
| Manufacturing type     | Herstellungsart             | Mode fabrication        | Productie methode       | tufted 5/16"   |                    |                    |
| Construction           | Struktur                    | Structure               | Structuur               | shaggy         |                    |                    |
| Pile composition       | Polmaterial                 | Couche d'usure          | Poolsamenstelling       | 100% PA        |                    |                    |
| Dye method             | Farbgestaltung              | Coloration              | Kleurverwerking         | piece dyed     |                    |                    |
| Primary backing        | Trägermaterial              | Premier dossier         | Tuftdoek                | woven          |                    |                    |
| Secondary backing      | Rückenausrüstung            | Dossier                 | Rug                     | action backing |                    |                    |
| Pile weight            | Poleinsatzgewicht           | Poids de velour         | Poolgewicht             | ISO 2424       | g/m²               | 800 (+/-)          |
| Total weight           | Gesamtgewicht               | Poids total             | Totaal gewicht          | ISO 8543       | g/m²               | 1.600 (+/-)        |
| Pile height            | Polhöhe                     | Hauteur du velours      | Poolhoogte              | ISO 1766       | mm                 | 20 (+/-)           |
| Total height           | Gesamtdicke                 | Epaisseur totale        | Totale dikte            | ISO 1765       | mm                 | 22 (+/-)           |
| Tuft density           | Noppenzahl                  | Nombre de touffes       | Aantal punten           | ISO 1763       | /m²                | 55.000 (+/-)       |
| Size                   | Abmessung                   | Dimension               | Afmeting                |                | cm                 | 400                |
| Classification         | Klassifikation              | Classement              | Gebruiksklasse          | EN 1307        | 22+ heavy domestic |                    |
| Comfort rating         | Komfortklasse               | Classement confort      | Comfort klasse          | EN 1307        | LC 3               |                    |
| Castor chair           | Stuhlrolleneignung          | Chaise à roulettes      | Rolstoelgeschikt        | EN 985         |                    |                    |
| Stair suitability      | Treppeneignung              | Escaliers               | Trappengeschikt         | EN 1963        |                    |                    |
| Fire resistance        | Brennverhalten              | Comportement feu        | Brandgedrag             | EN 13501-1     | Cfl-S1 glued       |                    |
| Permanent antistatic   | Permanent Antistatisch      | Antistatique permanent  | Permanent antistatisch  | ISO 6356       | kV                 | ≤ 2,0              |
| Transversal resistance | Durchgangswiderstand        | Résistance transversale | Doorgangsweerstand      | ISO 10965      | Ω                  | ≥ 10 <sup>10</sup> |
| Thermal resistance     | Wärmedurchlaßwiderstand     | Résistance thermique    | Warmtedoorlaatweerstand | ISO 8302       | m²/K/W             |                    |
| Sound absorption       | Schallabsorptionsgrad       | Absorption phonique     | Geluidsabsorptie        | ISO 354        | α <sub>w</sub>     |                    |
| Impact sound reduction | Trittschallverbesserungsmaß | Isolation phonique      | Geluidsisolatie         | ISO 10140      | ΔL <sub>w</sub>    | 25 dB              |
|                        |                             |                         |                         | ISO 10140      | ΔL                 | (1000 Hz)          |
| Colour fastness light  | Lichtechtheit               | Solidité à la lumière   | Lichtechtheid           | ISO 105 B02    | ≥ 7                |                    |
| Rubbing fastness       | Reibechtheit                | Solidité au frottement  | Wrijfechtheid           | ISO 105 X12    | ≥ 4-5              |                    |

Scan the QR code  
and discover the collection.



**EN1307**  
for use as floorcovering  
in buildings (EN 14041)  
according to the  
manufacturer's specification

**CE**  
**13**  
**EN 14041**  
**DOP 000461-002**

