

Technical details wall-to-wall

Manufacturing type	Herstellungsart	Mode fabrication	Productie methode		tufted 1/10"		
Construction	Struktur	Structure	Structuur		structured loop pile		
Pile composition	Polmaterial	Couche d'usure	Poolsamenstelling		100% PA6 - TRIFORMA™+		
Dye method	Farbgestaltung	Coloration	Kleurverwerking		solution dyed		
Primary backing	Trägermaterial	Premier dossier	Tuftdoek		non-woven		
Secondary backing	Rückenausrüstung	Dossier	Rug		action backing		
Pile weight	Poleinsatzgewicht	Poids de velour	Poolgewicht	ISO 2424	g/m²	650	(+/-)
Total weight	Gesamtgewicht	Poids total	Totaal gewicht	ISO 8543	g/m²	1.875	(+/-)
Pile height	Polhöhe	Hauteur du velours	Poolhoogte	ISO 1766	mm	4,0	(+/-)
Total height	Gesamtdicke	Epaisseur totale	Totale dikte	ISO 1765	mm	5,7	(+/-)
Tuft density	Noppenzahl	Nombre de touffes	Aantal punten	ISO 1763	/m²	175.000	(+/-)
Size	Abmessung	Dimension	Afmeting		cm	400	(+/-)
Classification	Klassifikation	Classement	Gebruiksklasse	EN 1307		32	general commercial
Comfort rating	Komfortklasse	Classement confort	Comfort klasse	EN 1307		LC 1	
Castor chair	Stuhlrolleneignung	Chaise à roulettes	Rolstoelgeschikt	EN 985		A	intensive
Stair suitability	Treppeneignung	Escaliers	Trappengeschikt	EN 1963		A	intensive
Fire resistance	Brennverhalten	Comportement feu	Brandgedrag	EN 13501-1		Bfl-S1	glued
Permanent antistatic	Permanent Antistatisch	Antistatique permanent	Permanent antistatisch	ISO 6356	kV	≤ 2,0	
Transversal resistance	Durchgangswiderstand	Résistance transversale	Doorgangsweerstand	ISO 10965	Ω	≤ 10 ¹⁰	
Thermal resistance	Wärmedurchlaßwiderstand	Résistance thermique	Warmtedoorlaatweerstand	ISO 8302	m²/K/W	0,086	
Sound absorption	Schallabsorptionsgrad	Absorption phonique	Geluidsabsorptie	ISO 354	α _w	0,20	
Impact sound reduction	Trittschallverbesserungsmaß	Isolation phonique	Geluidsisolatie	ISO 10140	ΔL _w	25 dB	
				ISO 10140	ΔL	44 dB	(1000 Hz)
Colour fastness light	Lichtechtheit	Solidité à la lumière	Lichtechtheid	ISO 105 B02		8	
Rubbing fastness	Reibechtheit	Solidité au frottement	Wrijftechtheid	ISO 105 X12		4-5	wet/dry
Water fastness	Wasserechtheit	Solidité à l'eau	Waterechtheid	ISO 105 E01		5	colour/staining

Scan the QR code
and discover the
collection.



EN 1307

for use as floorcovering in buildings
(EN 14041) according to the
manufacturer's specification



22

EN 14041
DOP 00S98A-001



TRIFORMA +

TWISE

